



LUXURY CARPET TILES

E-MAJOR SQR

CONSTRUCTION

Structure
Struktur
Structuur

Tufted 1/10" Loop
Tufté 1/10" Bouclé
Getuftet 1/10" Schlinge
Getuft 1/10" Luspool

PILE MATERIAL

Couche d'usure
Polmaterial
Poolmateriaal

100% PA6 Solution Dyed Nylon

SECONDARY BACKING

Dossier
Rückenausstattung
Rug

Back2Back: Modified bitumen
10% recycled content included

TOTAL WEIGHT

Poids total
Gesamtgewicht
Totaal gewicht

Ca. 4.400 g/m²

PILE WEIGHT

Poids du velours
Poleinsatzgewicht
Poolgewicht

Ca. 640 g/m²

PILE ABOVE BACKING

Poids de velours utile
Polnutzschichtgewicht
Nuttig poolgewicht

Ca. 370 g/m²

TOTAL HEIGHT

Épaisseur totale
Gesamtdicke
Totale hoogte

Ca. 6,2 mm

PILE HEIGHT

Épaisseur du velours
Poldicke
Poolhoogte

Ca. 2,7 mm

PILE DENSITY

Densité du velours
Polrohndichte
Pooldichtheid

Ca. 0,137g/cm³

TUFT DENSITY

Nombre de touffes
Noppenzahl
Aantal punten

Ca. 140.000/m²

CLASSIFICATION

Classement
Klassifikation
Classificatie

EN 1307
33 - LC1

CASTOR CHAIR SUITABILITY

Emploi chaise à roulettes
Stuhlrolleneignung
Rolstoelgeschiktheid

EN 985
A: intensive use

FIRE RESISTANCE

Comportement au feu
Brennverhalten
Brandgedrag

EN 13501-1
B_{f1}-s1

FASTNESS TO LIGHT

Solidité à la lumière
Lichtechtheit
Lichtechtheid

ISO 105-B02
≥ 7

RUBBING FASTNESS

Solidité au frottement
Reibechtheit
Wrijftechtheid

ISO 105-X12
≥ 4

COLOUR FASTNESS TO WATER

Solidité à l'eau
Wasserechtheit
Waterechtheid

EN ISO 105-E01
≥ 4

THERMAL RESISTANCE

Résistance thermique
Wärmedurchlasswiderstand
Warmte-doorlaatweerstand

ISO 8302
0,065 m²K/W

IMPACT NOISE RATING

Isolation phonique
Trittschallverbesserungsmass
Geluidsisolatie

ISO 10140
ΔL_w: 24dB

SOUND ABSORPTION

Absorption phonique
Schallabsorptionsgrad
Geluidsabsorptie

ISO 354
α_w: 0.15

PERMANENT ANTISTATIC

Antistatique permanent
Permanent antistatisch
Permanent antistatisch

ISO 6356
≤ 2 kV

TRANSVERSAL RESISTANCE

Résistance transversale
Durchgangswiderstand
Doorgangsweerstand

ISO/DIS 10965
≤ 10⁹ Ohm

SIZE

Dimensions
Abmessung
Afmetingen

50 x 50 cm

PACKAGING


Emballage
Verpackung
Verpakking

Box: 5 m²
Pallet: 20 boxes

DIMENSIONAL STABILITY

Stabilité dimensionnelle
Dimensionsstabilität
Dimensionele stabiliteit

EN 986
max. 0,2%







032



047




090



093




097




096




098



072



078



012